

Ferroelectricity

18.59 The ferroelectric behavior of BaTiO_3 ceases above its ferroelectric Curie temperature because the unit cell transforms from tetragonal geometry to cubic; thus, the Ti^{4+} is situated at the center of the cubic unit cell, there is no charge separation, and no net dipole moment.