

19.17 Thermal conductivities are higher for crystalline than for noncrystalline ceramics because, for noncrystalline, phonon scattering, and thus the resistance to heat transport, is much more effective due to the highly disordered and irregular atomic structure.