

19.30 According to Equation 19.9, the thermal shock resistance of a ceramic piece may be enhanced by increasing the fracture strength and thermal conductivity, and by decreasing the elastic modulus and linear coefficient of thermal expansion. Of these parameters, σ_f and α_l are most amenable to alteration, usually by changing the composition and/or the microstructure.